

Product Specifications

PRODUCT FEATURES

- For HVAC and Plumbing Industrial, Commercial and Residential Use
- Closed Cell Insulation
- Proprietary Blend Coating for UV and Outside Tear Resistance
- For Outdoor Applications
- Available in a Wide Range of Inside Thicknesses and Diameters
- Full-Slit and Half-Slit Available
- Cost Effective
- Completely Recyclable
- High Tear Resistance
- Flexible Year-Round Pipe Protection from Freezing and Condensation
- Resistant to Mold Growth
- Non-Porous
- Fiber-Free
- Very Low Water Vapor Permeability - No Additional Vapor Barriers Required
- Manufactured without CFCS, HCFCs, HFCS, PBDEs and Formaldehyde
- Indoor Air Quality: Low VOC, Fiber-Free, Non-Particulating, Formaldehyde-Free Insulation



Properties

Values

Maximum Use Temperature	220 F (104 C)
Minimum Use Temperature	-297 F (-183 C)
Density	1.2 to 2.0 PCF Nominal
Flame/Smoke	Less than 25/50 (ASTM E-84)
	Up to 1" wall thickness (coated)
	Passes MVSS302
Color	Black/Grey/White
Compressive Strength @ 25%	3.5-5 PSI
Tensile Strength	30 PSI
Elongation	150%
Thermal Stability	Less than 3% Linear shrinkage
Odor Emission	No objectionable odor
Weather Resistance	Passes ASTM C1775

Insulation ID Nominal	Foam Pipe Insulation R Values	
	1/2" Wall	3/4" Wall
1/4"	4.87	7.50
3/8"	4.35	6.69
1/2"	4.04	6.18
5/8"	3.79	5.79
3/4"	3.67	5.65
7/8"	3.53	5.33

Compatible with common types of piping — copper, steel, PVC, CPVC, PEX

Approvals, Certifications, Compliances:

ASTM C 1427, Type 1 (Tubes)
 Can be used in Plenum
 Conforms to ASHRAE 90.1 Energy Standards
 Building codes conformation:
 International Energy Conservation Code (IECC)
 International Mechanical Code (IMC)
 California title 24 Building Energy Efficiency Standards

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, PTI does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. PTI also does not assume any liability towards any person resulting from the use of said data or technical information. PTI reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for